

### GMC-Putty m

#### Repair and Maintenance Putty

#### GENERAL DESCRIPTION

**GMC-Putty m** is a long pot life version of our **GMC-Putty**. It is a rugged and durable putty like material. It provides good abrasion resistance at a moderate price. It can be built up to a thickness of ½ in or more in one coat. It is generally used when a putty material is applied with a grout pump then troweled smooth.

#### FEATURES

- Good chemical and thermal resistance
- Good resistance to abrasion
- Long term flexibility
- Good resistance to cavitation
- Easily built up for thick applications

#### PACKAGING

1 kg, 4 kg, and 10 kg units

#### COVERAGE

**GMC-Putty s** is a trowel-on rebuilding compound and can be applied up to 500 mils/coat. Theoretical coverage at 125 mils is 1.6 sq ft per kg.

#### MIXING RATIO

4.6 parts base (B) to 1.0 part (A) hardener by weight

#### POT LIFE

For a 1 kg. unit, mix at 70°F, pot life is approximately 90 minutes. Higher temperatures or larger mass will shorten this time, lower temperatures or smaller mass will extend it. Pot life can also be extended by spreading the mass out to dissipate heat.

#### COLORS

**GMC-Putty m** is white in color.

#### TECHNICAL DATA AND INFORMATION

##### Basic Chemical Resistance at Room Temperature:

Inorganic Acids	Good
Organic Acids	Good
Solvents	Fair
Alkalis	Excellent
Salts	Excellent
Alcohols	Good
Hydrocarbons	Good

##### Typical Physical Properties of Cured System:

Density	1.30
% Solids	100
Tensile Strength @ 70°F	13,500 psi
Tensile Shear @ 70°F	3,500 psi
Max. Dry Operating Temp	325 °F
Operating pH Range	1.0-14.0

#### SURFACE PREPARATION

- For maximum adhesion, material should be applied to a firm, clean, dry and abraded surface.
- Best results will be obtained by abrasive blasting the surface.
- If blasting is impractical, a grinding wheel, needle gun, or very stiff wire brush may be used.
- Clean greasy, oily or waxed surfaces with suitable solvent before applying material.

#### MIXING

Mix ALL of Part A with ALL of Part B. Mixing may be done on a large mixing board or container large enough to hold both the base and hardener. The selected mixing surface must be clean and dry. Mix the material thoroughly until no streaks of any kind are visible. If materials are cold, warm them to 70°F before mixing.



QUALITY SYSTEM  
REGISTERED TO  
ISO 9001:2000



NSF-ISR's Registration Program  
is Accredited by Member of the  
IAF MLA for QMS.

## CLEANUP

All mixing and applications tools should be immediately wiped or scraped clean when finished with using.

## APPLICATION

**GMC-Putty m** is best applied with a squeegee, trowel or the plastic applicator supplied with the kit. Press material thoroughly into substrate and insure a completely wetted out surface. Build up to the required thickness with a second pass. Large cracks or holes should be bridged with glass or metal cloth. Reinforcement should be overcoated.

For best results, do not apply:

- When temperature is below 50°F.
- When humidity is over 90%
- When there is moisture on the surface
- When surface temperature is not 5°F above dew point

## OVERCOATING

For pinhole control and/or thicker buildup, two or more coats may be employed. **GMC-Putty m** may be overcoated with other **DUROMAR** materials such as **EAC** or **EXP** for enhanced smoothness or increased chemical resistance. Overcoating may begin as soon as the first coat is firm enough to accept a second coat. In high humidity or cold temperatures a blush may develop which should first be wiped down with clean water. The following table is an approximate guide to the earliest and latest times an overcoat may be applied:

### GMC-Putty m Overcoat Windows

55°F	70°F	80°F
18 - 120 hrs.	10 - 96 hrs.	8 - 72 hrs.

At 70°F, if 72 hours have elapsed or the material is dry to the touch, it must be roughened before overcoating. The preferred method is a light abrasive brush blasting. Other treatments are light sanding, grinding or wire brushing.

## Q/C

The material should be visually inspected just after application and touched up where necessary. The material may also be spark tested if necessary.

## CURE SCHEDULE (@ 70 °F)

Tack Free:	10 hours
Functional Cure:	24 hours
Full Cure:	96 hours

## FORCE CURING

Force cures are recommended for severe service conditions as both the physical and chemical properties are enhanced. Force curing should not start until material has firmly set.

Recommended Force Cure Schedule:

- 1 hour at 250°F
- 4 hours at 180°F
- 8 hours at 120°F

## STORAGE

Store in dry area in closed containers between 50°F and 110°F. Shelf life at these conditions is greater than one year.

## HEALTH AND SAFETY

READ AND UNDERSTAND ALL MATERIAL GIVEN IN THE MSDS SHEETS BEFORE USING THE PRODUCT.

**GMC-Putty m** DOES NOT CONTAIN ANY FLAMMABLE MATERIAL OF ANY KIND. HOWEVER, THE MATERIAL IS COMBUSTIBLE. IN THE EVENT OF A FIRE, DRY POWDER, FOAM, OR CARBON DIOXIDE FIRE EXTINGUISHERS SHOULD BE USED. FIRE FIGHTERS SHOULD WEAR RESPIRATORS.

USE PROTECTIVE GLOVES AND EYEGLASSES WHEN USING.

USE IN AREAS OF GOOD VENTILATION.

## LIMITED WARRANTY

All recommendations covering the use of this product are based on past experience and laboratory findings. Methods or conditions of application and use of the product are beyond our control. We assume responsibility only for the uniformity of our product within normal manufacturing balances.

All Duromar products are formulated based on over 25 years of experience, laboratory tests, material data, field installations, and technical publications, which we believe to be, to the best of our knowledge, accurate and reliable. This information is intended to be used for guidance only. Because the only true reliable test is one that is in actual operation, Duromar will make available at no charge samples of materials for that testing purpose. Duromar, Inc. has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Duromar, Inc. does, therefore, not accept any liability arising from loss, injury, or damage resulting from such use or the contents of this data sheet (unless there are written agreements stating otherwise). The data contained herein is liable to modification as a result of practical experience and continuous product development. This data sheet replaces and annuls all previous issues, and it is, therefore, the user's responsibility to ensure that this sheet is current prior to using the product.



QUALITY SYSTEM  
REGISTERED TO  
ISO 9001:2000



NSF-ISR's Registration Program  
is Accredited by Member of the  
IAF MLA for QMS.