

# MG-F

## Machineable Putty

### GENERAL DESCRIPTION

**MG-F** is a stainless steel filled putty, which is engineered for use where final precision machining is required. Typical applications include shaft repairs, pump parts, bearing housings, or anywhere requiring final machining to close tolerances.

### FEATURES

- Easily machined
- Very good wear resistance
- Excellent corrosion resistance
- Good temperature resistance
- Easily worked with in thick applications
- Excellent compressive strength
- Machineable with conventional tools

### PACKAGING

1 kg and 4 kg. units

### COVERAGE

**MG-F** can be applied up to 1 inch or more. Theoretical coverage at 40 mils in thickness is 38 cubic inches per kg.

### MIXING RATIO

3 parts base (B) to 1 part hardener (A) by weight  
3 parts base (B) to 1 part hardener (A) by volume

### POT LIFE

For a 1 kg. unit, mix at 70°F, pot life is approximately 25 minutes. Higher temperatures or larger mixes will shorten this time. Lower temperatures or smaller mixes will extend it. Pot life can also be extended by spreading out the mass to dissipate heat.

### COLORS

**MG-F** is steel grey in color.

### TECHNICAL DATA AND INFORMATION

#### Basic Chemical Resistance at Room Temperature:

Inorganic Acids	Good
Organic Acids	Good
Solvents	Good
Alkalis	Excellent
Salts	Excellent
Alcohols	Excellent
Hydrocarbons	Excellent

#### Typical Physical Properties of Cured System:

Density	1.62
% Solids	100
Flexural Strength @ 70°F	17,600 psi
Tensile Strength @ 70°F	11,500 psi
Tensile Shear @ 70°F	3,000 psi
Compressive Strength @ 70°F	18,000 psi
Service Temperature Maximum	300°F
Operating pH Range	1.5-14.0

### SURFACE PREPARATION

The area to be repaired should be machined down so that it is undercut to a minimum of 1/16 of an inch. The surface of the cut should be rough; a thread pattern or gramophone cut should be used. The ends of the cut should be keystoneed or undercut as far as the bit can cut, leaving a fine edge on the shaft. After machining, the area must be thoroughly cleaned with **MEK** or similar solvent to remove all traces of cutting or lubricating agents.

### MIXING

Mix ALL of Part A with ALL of Part B. Mixing may be done in a container large enough to hold both the base and hardener. The selected container must be clean and dry. Mix the material thoroughly until no streaks of any kind are visible. If materials are cold, warm them to 70°F before mixing.



QUALITY SYSTEM  
REGISTERED TO  
ISO 9001:2000



NSF-ISR's Registration Program  
is Accredited by Member of the  
IAF MLA for QMS.

## APPLICATION

**MG-F** is best applied with the spatula or plastic applicator supplied with the kit. The material should be thoroughly and firmly pressed into the threads to insure a completely wetted out surface. Particular attention should be given to the undercut or keystone areas at the edge of the cut. Build up to approximately 40-60 mils proud beyond the required thickness.

For best results, do not apply:

- When temperature is below 40°F.
- When humidity is over 95%
- When there is moisture on the surface
- When surface temperature is not 5°F above dew point

## MACHINING SPECIFICATIONS

### TURNING

Surface Cutting Speed:	2600 in/min
Feed Rate for Roughing:	40 thou/rev
Feed Rate for Finishing	10 thou/rev
Tool:	Firth Brown TTA Code
Top Rake:	3 degrees
Side Clearance:	3 degrees
Front Clearance:	3 degrees
Comparison with mild steel and aluminum:	30% longer tool life
Comparison with casting:	
Alloy and zinc:	Comparable
Comments:	Cut dry

### KEYWAY MACHINING-VERTICAL MILLING

Cutter Speed:	520 rpm minimum 3300 in./min. for 2 inch cutter
Table Traverse:	3-6 in./min.
Tool:	High speed steel standard end mills
Rake:	Standard
Comparison with mild steel and aluminum:	30% longer tool life
Comparison with casting:	
Alloy and zinc:	Comparable
Comments:	Cut dry

### SLOT DRILLING FLAT OR SLOT

Cutter Speed:	400 rpm, 2600 in./min. for 2 inch cutter
Table Traverse:	6 in./min.
Tool:	High speed steel
Comparison with mild steel and aluminum:	30% longer tool life
Comments:	Cut dry

## OVERCOATING

For thicker buildup two or more coats may be employed. Overcoating may commence as soon as the first coat is firm enough to accept a second coat, but no later than the point where a tack free film is evident.

## Q/C

The material should be visually inspected just after machining, and if necessary, touched up and re-machined.

## STORAGE

Store in dry area in closed containers between 50°F and 110°F. Shelf life at these conditions is greater than one year.

## HEALTH AND SAFETY

READ AND UNDERSTAND ALL MATERIAL GIVEN IN THE MSDS SHEETS BEFORE USING THE PRODUCT.

**MG-F DOES NOT CONTAIN ANY FLAMMABLE MATERIAL OF ANY KIND. HOWEVER, THE MATERIAL IS COMBUSTIBLE. IN THE EVENT OF A FIRE, DRY POWDER, FOAM, OR CARBON DIOXIDE FIRE EXTINGUISHERS SHOULD BE USED. FIRE FIGHTERS SHOULD WEAR RESPIRATORS.**

USE PROTECTIVE GLOVES AND EYEGLASSES WHEN USING.

USE IN AREAS OF GOOD VENTILATION.

## LIMITED WARRANTY

All recommendations covering the use of this product are based on past experience and laboratory findings. Methods or conditions of application and use of the product are beyond our control. We assume responsibility only for the uniformity of our product within normal manufacturing balances.

All Duromar products are formulated based on over 25 years of experience, laboratory tests, material data, field installations, and technical publications, which we believe to be, to the best of our knowledge, accurate and reliable. This information is intended to be used for guidance only. Because the only true reliable test is one that is in actual operation, Duromar will make available at no charge samples of materials for that testing purpose. Duromar, Inc. has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Duromar, Inc. does, therefore, not accept any liability arising from loss, injury, or damage resulting from such use or the contents of this data sheet (unless there are written agreements stating otherwise). The data contained herein is liable to modification as a result of practical experience and continuous product development. This data sheet replaces and annuls all previous issues, and it is, therefore, the user's responsibility to ensure that this sheet is current prior to using the product.

Rev. 11/07



QUALITY SYSTEM  
REGISTERED TO  
ISO 9001:2000



NSF-ISR's Registration Program  
is Accredited by Member of the  
IAF MLA for QMS.